PRODUCT DATASHEET

Bitumen 60/70

Paving-grade bitumen for hot-mix asphalt and general road construction.

Typical specification

Property	Test method	Typical limit
Penetration @ 25°C	ASTM D5	**60–70 dmm**
Softening point	ASTM D36	**48–56 °C**
Ductility @ 25°C	ASTM D113	**≥ 100 cm**
Flash point (COC)	ASTM D92	**≥ 232 °C**
Solubility in TCE	ASTM D2042	**≥ 99 %**
Loss on heating	ASTM D6	**≤ 0.2 %**

Values are typical limits per the referenced standards and may vary by batch. The certificate of analysis supplied with each shipment is the binding specification. Handle hot bitumen with appropriate PPE and follow the safety data sheet.

Prime Bitumen Limited
Colfax Industrial Area, Bonje, Mombasa, Kenya
+254 752 013 343 | Adel@primebitumenke.com