PRODUCT DATASHEET

PMB

Polymer-modified bitumen for highways, heavy traffic and high temperatures.

Typical specification

Property	Test method	Typical limit
Penetration @ 25°C	EN 1426	**45–80 dmm**
Softening point	EN 1427	**≥ 65 °C**
Elastic recovery @ 25°C	EN 13398	**≥ 70 %**
Fraass breaking point	EN 12593	**≤ −15 °C**
Flash point	EN ISO 2592	**≥ 220 °C**
Storage stability (Δ softening point)	EN 13399	**≤ 5 °C**

Values are typical limits per the referenced standards and may vary by batch. The certificate of analysis supplied with each shipment is the binding specification. Handle hot bitumen with appropriate PPE and follow the safety data sheet.

Prime Bitumen Limited
Colfax Industrial Area, Bonje, Mombasa, Kenya
+254 752 013 343 | Adel@primebitumenke.com